



DESIGN <i>[Signature]</i>	DRAWN BY <i>[Signature]</i>	DART AEROSPACE LTD HAWKESBURY, ONTARIO, CANADA	
CHECKED <i>[Signature]</i>	APPROVED <i>[Signature]</i>	DRAWING NO. DSI 9187	REV. A SHEET 1 OF 1
DATE 00.10.05		TITLE COMPOSITE DAMAGE LIMITS	SCALE NTS
A	00.10.05	NEW ISSUE	

DART SERVICE INSTRUCTION

TO AMEND MMS-D407-627 REV. A OR REV. B
REF. CANADIAN STC: SH98-57

AND

TO AMEND MMS-D350-602 REV. A OR REV. B
REF. CANADIAN STC: SH93-97
REF. US FAA STC: SR01144NY

ADD THE FOLLOWING INSPECTION TO THE APPLICABLE MAINTENANCE MANUAL
SUPPLEMENTS:

300 HOUR INSPECTION

To be performed every 300 hours or if damage found on Daily Inspection.

Inspect the composite base and lid of the **Heli-Utility-Pod™** for mechanical damage (cracks, holes, voids, dents, delamination) in accordance with Table 1 and repair in accordance with the Dart Composite Repair Manual QSI 037. Replace parts damaged beyond limits in accordance with MMS-D407-627 / MMS-D350-602.

Table 1. – Composite Damage Limits

Damage	Limit	Repair Scheme
Holes in Composite Skin	4" x 4" area	QSI 037 Section 9.1
Holes in Foam Core	2" x 2" area	QSI 037 Section 9.2
Dents in Foam Core	2" x 2" area	QSI 037 Section 9.3
Edge Damage	2" x 2" area	QSI 037 Section 9.4
Delamination	2" x 2" area	QSI 037 Section 9.5
Edge Crack	1" long crack	QSI 037 Section 9.6
Skin Crack	2" long crack	QSI 037 Section 9.7
Void	2" x 2" area	QSI 037 Section 9.8

Copyright © 2000 by DART AEROSPACE LTD

THIS DOCUMENT IS PRIVATE AND CONFIDENTIAL AND IS SUPPLIED ON THE EXPRESS CONDITION THAT IT IS NOT TO BE USED FOR ANY PURPOSE OR COPIED OR COMMUNICATED TO ANY OTHER PERSON WITHOUT WRITTEN PERMISSION FROM DART AEROSPACE LTD.